

5190243IB02

2022082630



Test Result : B,s2,d0

Report No : 2022082630
Applicant : SIMONA PLASTECH LEVHA SAN. A.Ş.
Contact Person : Onur SİMİT
Telephone : +380 553 80 08
E-Mail : onur.simit@simona-group.com
Sample Accepted on : 20.08.2022
Report Date : 26.08.2022
Total Number of Pages : 6 (Pg)

Sample ID : SIMOPOR SP 3 mm PVC FOAM

	TEST	METHOD	RESULT
*	Fire classification of construction products and building elements-Part 1: Classification using test data from reaction to fire tests.	EN 13501-1	PASS
			B s2 d0



Seal

K. rveli

Customer Representative
Merve Nur KIRVELİ

M. Özler

Laboratory Manager
Merve ÖZLÜ

RESULTS

1.TS EN ISO 13501-1

Building products and structural elements, fire classification. Part 1: Classification by using data obtained from the behavior tests against fire.

This standard covers the behavior of all building products, including products used in combination with structural elements, against flame.

Provisions for Inspection and Test:

If Rule / Test Is Not Needed To Be Applied To Sample (Not Applicable To Sample)

If the Specimen Fits the Rules (Passed)

If the Specimen Tested Does Not Comply with the Rules (Left)

If there is a Rule / Experiment Not Applied for Any Reason (Unable)

NU

P

K

Y

Sample No	1	2	
Flammability (Yes/No)	No	No	
Whether the flame is spread (Yes/No)	No	No	
Flame Spreading Time	4sec	4sec	
Combustion on Filter Paper (Yes/No)	No	No	

Related Product Standard and Citations: Fire Response Test (EN 13501-1 B Class)

Conditioning Details: The test samples were conditioned at 23 ± 2 ° C and $50 \pm 5\%$ relative humidity at EN 13238 according to 4.3 C..

Class B (TS EN ISO 13501-1 Clause 8.3)	For the determination of conformity to Class <i>B</i> , use a product, the time of exposure to flame according to TS EN 13501-1
Test Sample	Length -- mm , Width -- mm , Thickness — mm
Exposure Requirements	Surface exposed to flame

Reaction to fire

The combustion class (Euroclasses) of the product must be determined in accordance with EN 13501-1.

TS EN 13501-1 - Flammability Test (TS EN ISO 1182)

This test is carried out to determine whether a contribution to a fire is significant, regardless of the end use of a product.

Material	Rule / Test	Result / Evaluation	Decision
5	Test sample		
	---	---	PASS
6	Conditioning		
	<p>Test samples shall be conditioned as specified in EN 13238. The test samples should be dried and tested for 20 hours to 24 hours in an air-circulating oven with a temperature of $(60 \pm 5) ^\circ \text{C}$.</p> <p>it must be allowed to cool to ambient temperature in a desiccator before being held. The mass of each sample should be determined with a sensitivity of 0.01 g before the experiment.</p>	<p>Conditioning Time: 1 week Conditioning Temperature: $23 \pm 2 ^\circ \text{C}$ Conditioning Humidity: $50 \pm 5\%$ EN 13238 4.3 Conditioning for fixed period a) Minimum conditioning period of one weeks: 2) cement based products;</p>	PASS
8	Display of results		
8.1	The mass loss measured mass loss is calculated and recorded in% for each of the three test samples.	1. test	2.12 MJ/kg
8.2	Flammability The measured total time of continuous exacerbation is calculated and recorded in seconds for each of the three test samples.	TS EN ISO 11925-2	
8.3	Note 1: TS EN 13501 -1 Class A_1 Homogeneous and non-homogeneous products must meet the $1t \leq 30 ^\circ \text{C}$ and $m_{\text{ve}} \leq 50\%$ and $t_f = 0\text{s}$ criteria.	2. test	2.13 MJ/kg
	Note 2: TS EN 13501-1 Class A_1 Homogeneous and non-homogeneous products must meet the $\Delta t \leq 50 ^\circ \text{C}$ and $\Delta m_{\text{olmayan}} \leq 50\%$ and t_f Sınıf 20s criteria.	TS EN ISO 11925-2	
	Note 3: TS EN 13501-1 Class A_1 Homogen products shall meet the PCS ojen 2.0 MJ / kg criteria.	3. test	2.14 MJ/kg
		TS EN ISO 11925-2	N/A

Classification of **SIMOPOR SP 3 mm PVC FOAM** according to TS EN 13501-1 according to the behavior against fire:

B

Test method	Parameter	Number of tests	Mean of continuous parameter	Results Suitable parameter
TS EN 13823	FIGRA _{0,4MJ} (W/s)	2	98	≤120
	LFS < side	2	(-)	No
	THR _{600s} (MJ)	2	6,9	≤7,5
	SMOGR (m ² /s ²)	2	18	≤180
	TSP _{600s} (m ²)	2	27	≤200
	Drops and droplets (s)	2	(-)	No

Test method	Parameter	Parameter	Compliance criteria
TS EN 13823	FIGRA _{0,2 MJ} [W/s]	98	≤120 (B)
	THR _{600s} (MJ)	6,9	≤7,5 (B)
	LFS < side	(-)	No
	SMOGR [m ² /s ²]	18	≤180 (s2)
	TSP _{600s} [m ²]	27	≤200 (s2)
	burning drops / particles burning time (s)	No	No (d0)

Classification of SIMOPOR SP 3mm PVC FOAM based on fire behavior:

B

Additional classification for smoke formation:

s2


Additional classification for burning drops / beads:

d0

Reaction to fire for **SIMOPOR SP 3 mm PVC FOAM**

<u>Flammability Behavior</u>		<u>Smoke</u>		<u>Burning Drops</u>	
B	-	s	2	-	d 0

SAMPLE IMAGE



**** End of Report ****